



**1. Product Name**

QUIKRETE® Commercial Grade FastSet™ Repair Mortar #1241-60

**2. Manufacturer**

The QUIKRETE Companies  
 One Securities Centre  
 3490 Piedmont Rd., NE, Suite 1300  
 Atlanta, GA 30305  
 (404) 634-9100  
 Fax: (404) 842-1424  
 www.quikrete.com

**3. Product Description**

**BASIC USE**

QUIKRETE® FastSet™ Repair Mortar is a Portland cement based high strength mortar specially formulated to make structural repairs to any concrete or masonry surface. It provides low sag making it ideal for vertical or overhead repairs.

Its unique properties allow the user to actually sculpt the material during application. Use to repair concrete cracks, curbs, steps, prestress panels, pipe, tunnels, sewers, loading docks, silos, retaining walls, culverts, catch basins, decorative moldings, bridge columns, parapet walls, septic tanks, cold storage vaults, virtually any vertical or overhead concrete surface.

**LIMITATIONS**

- Do not apply when temperatures are below 40 degrees F (4 degrees C) or are expected to drop below 32 degrees F (0 degrees C) within 24 hours
- In hot weather, use cool mixing water to lengthen setting time
- Mix no more material than can be used in 15 minutes
- Do not retemper with additional water

**SIZE**

- 60 lb (27.2 kg) bags

**YIELD**

A 60 lb (27.2 kg) bag of QUIKRETE FastSet Repair Mortar will yield 0.54 cu ft (15 L) of material. QUIKRETE FastSet Repair Mortar can be extended with up to 30 lb (13.6 kg) of -1/2"

(-12.7 mm) maximum size aggregate for deep repairs.

**4. Technical Data**

**APPLICABLE STANDARDS**

ASTM International

- ASTM C109/C109M Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or (50-mm) Cube Specimens)
- ASTM C191 Standard Test Method for Time of Setting of Hydraulic Cement by Vicat Needle
- ASTM C882 Standard Test Method for Bond Strength of Epoxy-Resin Systems Used With Concrete By Slant Shear
- ASTM C928 Standard Specification for Packaged, Dry, Rapid-Hardening Cementitious Materials for Concrete Repairs

**PHYSICAL/CHEMICAL PROPERTIES**

Typical test results for QUIKRETE FastSet Repair Mortar, when tested in accordance with applicable ASTM Test Methods, are shown in Table 1. Product meets the requirements of ASTM C928 Type R2 except for flow which is

TABLE 1 QUIKRETE FASTSET™ REPAIR MORTAR PHYSICAL PROPERTIES

Setting time, ASTM C191	
Initial	Approx. 20 min.
Final	20 - 40 min.
Approx. water content per 1 3/8 gal (5.2 L) bag	
Consistency	gel-like
Unit weight, lb/cu ft (kg/m³)	128 (2051)
Compressive strength, ASTM C109 modified	
3 hours	2000 psi (13.8 MPa)
24 hours	4000 psi (27.6 MPa)
7 days	5000 psi (34.5 MPa)
28 days	6000 psi (41.4 MPa)
Slant shear, ASTM C882 modified	
24 hours	1000 psi (6.9 MPa)
7 days	1500 psi (10.3 MPa)
28 days	2500 psi (17.2 MPa)

**Application to overhead surfaces**

Can be built up to at least 1 1/2" (38 mm) in 1 application



QUIKRETE® Commercial Grade FastSet™ Repair Mortar #1241-60

intentionally reduced to make it suitable for overhead application.

**5. Installation**

**SURFACE PREPARATION**

- Remove all spalled areas, as well as areas of unsound concrete and previous patching materials
- Holes should be chipped out to create a new sound substrate
- If rusty reinforcing steel is present, it must be abrasive blasted to remove rust. In many cases, it will be best to remove enough material to completely expose the reinforcing steel
- Large vertical or overhead patches deeper than 2" (51 mm) should contain reinforcing steel. If none is present, new steel should be inserted using appropriate techniques
- Holes should be dampened with clean water before patching. No puddles of water should be left in the hole

**MIXING**

- Add approximately 1 3/8 gal (5.2 L) of water to the mixer for each 60 lb (27.2 kg) bag of QUIKRETE FastSet Repair Mortar being mixed
- Add the product and mix for approximately 3 minutes. Adjust water as needed to achieve a stiff gel-like consistency
- Where large quantities of material are used for patches deeper than 2" (51 mm), QUIKRETE FastSet Repair Mortar may be extended with 30 lbs (13.6 kg) of -1/2" (-12.7 mm) aggregate per 60 lb (27.2 kg) bag. This will require approximately 6 qt (5.7 L) of water depending on the dampness of the aggregate

**APPLICATION**

QUIKRETE FastSet Repair Mortar should be trowel applied to the damp surface. Apply a thin layer with heavy trowel pressure, and then go back and build up to the desired thickness. QUIKRETE FastSet Repair Mortar obtains high bond strength without the use of bonding adhesives or acrylic additives. After initial set, the material may be trimmed and shaped to match the existing contours of the patch area.

**CURING**

During the first 24 hours, it is best to keep the patch covered or damp to prevent excessive loss of water.

Under hot, dry and windy placing conditions, all concrete tends to lose moisture unevenly and may develop plastic shrinkage cracks. The use of sheeting, monomolecular films (either sprayed or rolled on), as well as application of a very fine fog spray of water, has been quite successful in arresting shrinkage cracking.

**6. Availability**

QUIKRETE FastSet Repair Mortar is available at leading concrete construction supply houses and distributors. Contact QUIKRETE Construction Products for the name of the nearest dealer.

**7. Warranty**

The QUIKRETE Companies warrant this product to be of merchantable quality when used or applied in accordance with the instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of its product (as purchased) found to be defective, or at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given to The QUIKRETE Companies in writing. The limited warranty is issued and accepted in lieu of all other express warranties and expressly excludes liability for consequential damages.

**8. Maintenance**

None required.

**9. Technical Services**

The QUIKRETE Companies maintain technical field representatives throughout the country. Contact a local distributor for the name and number of the nearest representative or call QUIKRETE Construction Products.

**10. Filing Systems**

- First Source™
- Additional product information is available from the manufacturer.