



PACKAGE PAVEMENT™

FIELDSTONE MIX

- 1. Product Name:** Fieldstone Mix
- 2. Item Code:** 90569
- 3. Manufacturer:**
 Package Pavement Co., Inc.
 675 Leetown Road, PO Box 408
 Stormville, NY 12582
 (800) 724-8193
 FAX (845) 221-0433
 www.packagepavement.com

4. Product Description

Fieldstone Mix is a high strength masonry product specifically designed to bond to natural stone used in construction. It has been developed in conjunction with experienced masons and produced with the highest quality masonry materials.

When Fieldstones are used in walls and buildings they are irregular in shape and chemical content. These stones usually has a greater density and a less porous bonding surface than brick or block and are subject to the harshest weather conditions. The mortar that binds this stone needs to be designed for these extremes. Package Pavement Fieldstone Mix is the solution.

5. Technical Data

Fieldstone Mortar is a custom mortar blend consisting of masonry cement, portland cement and mason sand. Compressive Strength data follows below:

TECHNICAL DATA		
COMPRESSIVE STRENGTH:		
3 DAY	_____	2400 psi
7 DAY	_____	2650 psi
28 DAY	_____	3920 psi
<small>ACTUAL RESULTS MAY VARY DUE TO WORKMANSHIP, REGIONAL MATERIAL VARIATIONS, AND JOBSITE CONDITIONS.</small>		

7. Curing

Proper curing increases strength and durability of masonry or concrete work. See ASTM C-270 Section X1.9.5.4. To achieve maximum strength, a very light wetting of the in-place masonry, such as a fog spray, can improve its quality. Curing requirements will vary depending on stone used and weather conditions.

8. Safety and Handling

Always wear dust masks, goggles, and gloves while using Fieldstone Mix. Exposure to Portland, hydrated lime and sand dust over long periods of time can cause silicosis. The alkalinity of Portland and hydrated lime can also cause severe burns if used without personal protection. If the product comes in contact with eyes, rinse them thoroughly with water and see a physician without delay.

9. Caution

Do not apply if rain is forecast within 24 hours of the application or temperatures are expected to go below freezing (use above 40°F).

10. Warranty

Package Pavement warrants this product to be of merchantable quality when used in accordance with the instructions herein. We will not be liable for incidental or consequential damages, as defined under the uniform commercial code, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or other than the intended use. User shall determine the suitability of the product for its intended use and user alone assumes all risks and liabilities in connection therewith. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from the date it was, or reasonably should have been, found.

6. Installation

1. Prior to application of Fieldstone Mortar, make sure the stone surface is very clean and free of debris.
2. Blend Fieldstone Mortar with approximately 15% water and spread evenly over the stone joint area. Make sure all voids between the stones are completely filled.
3. Once the joints are filled, remove all excess mortar from the surrounding surface.

